CLAIMS

What is claimed is:

1. A flowable materials container comprising:

a body of a cyclic olefin containing polymer or a bridged polycyclic olefin containing polymer, the body defining a chamber to contain flowable materials, the chamber having an opening;

an elastomeric component attached to the body and providing a seal of the chamber; and

wherein the body when filled with 1 ml of water suitable for injection and sealed with the elastomeric component and stored for 3 months generates less than 4 ppm of chlorides in the water.

- 2. The container of claim 1 wherein the body is a syringe body.
- 3. The container of claim 2 wherein the elastomeric component is a plunger seal.
 - 4. The container of claim 1 wherein the elastomeric component is a synthetic rubber.
- 5. The container of claim 4 wherein the synthetic rubber is selected from the group consisting of styrene-butadiene copolymers, acrylonitrile-butadiene copolymers, neoprenes, butyl rubbers, polysulfide elastomers, urethane rubbers, stereo rubbers, ethylene-propylene elastomers.
- 6. The container of claim 5 wherein the synthetic rubber has halogen substitutents.
 - 7. The container of claim 6 wherein the synthetic rubber is a halogenated butyl rubber.
 - 8. The container of claim 7 wherein the synthetic rubber is a chlorobutyl-based elastomer.

20

- 9. A flowable materials container comprising:
- a body of a homopolymer, copolymer or terpolymer of norbornene, the body defining a chamber to contain flowable materials, the chamber having an opening; and an elastomeric component providing a seal of the opening and the component being a butyl rubber.
 - 10. The container of claim 9 wherein the body is a homopolymer of norbornene.
 - 11. The container of claim 9 wherein the body is a copolymer of norbornene.
- 12. The container of claim 11 wherein the copolymer of norbornene has a comonomer selected from the group consisting of α -olefins having from 2-10 carbons, aromatic hydrocarbons, cyclic olefins and bridged polycyclic olefins.
- 15 13. The container of claim 12 wherein the comonomer is ethylene.
 - 14. The container of claim 9 wherein the butyl rubber is halogenated.
 - 15. The container of claim 14 wherein the component is a chlorobutyl elastomer.
 - 16. The container of claim 15 wherein the component is essentially latex free.
 - 17. The container of claim 15 wherein the component is 100% latex free.
- 25 18. A syringe comprising:
 - a syringe body of a norbornene and ethylene copolymer, the body defining a chamber for containing water and having an opening; and
 - a plunger seal of a halobutyl based elastomer sealing the opening.
- 30 19. The syringe of claim 18 wherein the norbornene and ethylene copolymer has a heat deflection temperature at 0.45 Mpa from about 70°C to about 200°C.

- 20. The syringe of claim 18 wherein the norbornene and ethylene copolymer has a heat deflection temperature at 0.45 Mpa from about 75°C to about 150°.
- 21. The syringe of claim 18 wherein the norbornene and ethylene copolymer has a heat deflection temperature at 0.45 Mpa from about 76°C to about 149°C.

22. A syringe comprising:

a syringe body of a norbornene and ethylene copolymer, the body defining a chamber for containing water and having an opening;

a plunger seal of a halobutyl based elastomer sealing the opening; and wherein the syringe meets all requirements of the United States Pharmocopoeia for sterile water for injection.

- 23. A sterile water for injection syringe comprising:
- a syringe body of a norbornene and ethylene copolymer, the body defining a chamber containing water and having an opening;
 - a plunger seal of a halobutyl based elastomer forming a fluid tight seal of the opening; and

wherein the syringe meets all requirements of the United States Pharmocopoeia 20 for sterile water for injection.

- 24. The syringe of claim 23 wherein the plunger seal is a chlorobutyl based elastomer.
- 25. The syringe of claim 24 wherein the norbornene and ethylene copolymer has a heat deflection temperature at 0.45 Mpa from about 70°C to about 200°C.
 - 26. The syringe of claim 24 wherein the norbornene and ethylene copolymer has a heat deflection temperature at 0.45 Mpa from about 75°C to about 150°.
 - 27. The syringe of claim 24 wherein the norbornene and ethylene copolymer has a heat deflection temperature at 0.45 Mpa from about 76°C to about 149°C.

25

- 28. The syringe of claim 24 wherein the norbonrene and ethylene copolymer is capable of being sterilized in an autoclave at 121°C.
 - 29. A method for filling a syringe comprising the steps of:
- 5 providing a syringe body of a norbornene and ethylene copolymer and having an opening;

sterilizing the syringe body to define a sterilized syringe body;

transferring the sterilized syringe body to a sterile environment while maintaining the sterilized syringe body;

filling the sterilized syringe body with an appropriate quantity of sterile water for injection;

sealing the opening with an elastomeric component of a halobutyl based elastomer to define a sterile water for injection syringe; and

wherein the sterile water for injection syringe meets the requirements of the United States Pharmocopoeia for sterile water for injection.

- 30. The method of claim 29 wherein the norbornene and ethylene copolymer has a heat deflection temperature at 0.45 Mpa from about 70°C to about 200°C.
- 31. The method of claim 29 wherein the norbornene and ethylene copolymer has a heat deflection temperature at 0.45 Mpa from about 75°C to about 150°.
 - 32. The method of claim 29 wherein the norbornene and ethylene copolymer has a heat deflection temperature at 0.45 Mpa from about 76°C to about 149°C.
 - 33. The method of claim 32 wherein the halobutyl based elastomer is a chlorobutyl-based elastomer.
- 34. The method of claim 29 wherein the transferring step comprises the step of: transferring the sterilized syringe body from a sterilizing station to the sterile environment wherein the sterilized syringe body is exposed to a sterile ambient atmosphere.

35. A method for filling a syringe comprising the steps of:

providing a syringe body of a norbornene and ethylene copolymer and having an opening;

sterilizing the syringe body to define a sterilized syringe body;

transferring the sterilized syringe body to a sterile environment while maintaining the sterilized syringe body;

immediately filling the sterilized syringe body with an appropriate quantity of sterile water for injection;

sealing the opening with an elastomeric component of a halobutyl-based elastomer

to define a sterile water for injection syringe; and

wherein the sterile water for injection syringe meets the requirements of the United States Pharmocopoeia for sterile water for injection.